

# PVC Product Specification

Grade	K-Value	Polymerisation Degree	Bulk Density (g/cc)	Volatile matter (%)	Applications
SIP-57	57	720 ± 50	0.57 ± 0.05	Max 0.5	Rigid plates Various extruded sheets Draw films Blow bottles Calandring
SIP-65	65	1,030 ± 50	0.55 ± 0.05	Max 0.3	Pipes Corrugated sheets
SIP-65S	65	1,030 ± 50	0.52 ± 0.05	Max 0.3	Flexible films Films for foods Sheets Hosepipes, tapes Wires and cables
SIP-70	70	1,320 ± 50	0.49 ± 0.05	Max 0.3	Films for agricultural purposes General flexible films Sheets Leathers Wires and cables